

FIREPRO CENTABUILD INSULATION

HEAD OFFICE: AUCKLAND (09) 579 0367
CHRISTCHURCH (03) 379 9364
www.firepro.co.nz sales@firepro.co.nz

Product specifications
can change. Contact
us to ensure you have
our latest datasheet

INDUSTRIAL EQUIPMENT INSULATION FLEXIBLE GLASSWOOL BLANKET

DESCRIPTION

Rolls of flexible Insulation for thermal insulation and sound control of industrial equipment operating from subzero to 350°C. These are high performance glasswool products. Manufactured with consistent fibre diameter for excellent thermal and acoustical performance. IEI is available in 24Kg/M³ & 32Kg/M³ density glasswool. This is significantly higher density than glasswool blanket typically used in ceiling or wall insulation.

APPLICATION

Applications include the following:

- Heating equipment such as ovens, furnaces, and hot water generators.
- Cooling equipment such as air-conditioning, food processing freezers, and low temperature speciality equipment.
- Vessels, tanks and other storage facilities with operating temperatures from subzero to 350°C.

DURABLE

The glass fibres are incombustible. Being non-cellular and non-hygroscopic, they are resistant to the effect of moisture, oil, grease and most acids. The highly resilient glass fibres resist breakdown or sagging from vibration and yield readily to impact.

RESILIENT AND FLEXIBLE

The resilience of this product range minimizes the insulation's packing down and losing its effectiveness. The performance of any insulation is dependent upon installation. The flexibility makes it easy to apply, more manageable in difficult working areas, and more conformable to curved surfaces.

STRONG, AND EASY TO APPLY

Has high tensile strength and does not pull apart during normal handling. It can be pulled over corners, past hangers, through narrow openings, and formed around elbows, tees, etc. It is lightweight and easy to cut with an ordinary knife, and is readily attached to duct surfaces or equipment with adhesive or mechanical fasteners.

SIZES AVAILABLE

	Density (Kg.M ³)	Thickness (mm)	Width (M)	Length (M)
I.E.I 2524	24	25	1.2	24
I.E.I 5024	24	50	1.2	12
I.E.I. 2532	32	25	1.2	24
I.E.I. 5032	32	50	1.2	12

General Properties	
Temperature (maximum)	350°C
K value @ 24Kg/M ³ @24°C	W/M°C 0.0375
K value @ 32Kg/M ³ @24°C	W/M°C 0.0346
Thermal Resistance	
24Kg 25mm	0.67M ² °C/W
24Kg 50mm	1.33M ² °C/W
32Kg 25mm	0.72 M ² °C/W
32Kg 50mm	1.45 M ² °C/W
Moisture absorption	Less than 5% by weight
Alkalinity	PH9, slightly alkaline (PH7 is neutral)
Corrosivity (with steel, copper or aluminium)	Does not accelerate
Odour	None
Capillarity (after 24 Hours)	Negligible
Shrinkage	None
Resistance to fungi and bacteria	Does not promote

ACOUSTICAL PERFORMANCE

Density (Kg/M ³)	Thickness (mm)	Centre Frequency (Hz)						
		125	250	500	1000	2000	4000	NRC
24	25	0.24	0.36	0.67	0.87	0.88	0.92	0.7
32	25	0.19	0.35	0.71	0.86	0.94	0.97	0.7
24	50	0.36	0.64	1.04	1.06	1.05	1.1	0.95
32	50	0.38	0.72	1.11	1.07	1.04	1.07	1

NOTE: The technical information and suggestions for use and application presented herein represent the best information available to us and are believed to be reliable. If used beyond the situations detailed on this datasheet we advise confirming their suitability before installation. All dimensions are nominal.

We reserve the right to make changes or to withdraw designs and products without notice.